

## TECASON S - Stock Shapes

### Chemical Designation

PSU (Polysulfone)

### Colour

natural transparent

### Density

1.24 g/cm<sup>3</sup>

### Main features

- good heat deflection temperature
- 
- high strength
- high stiffness
- high dimensional stability
- electrically insulating
- resistance against high energy radiation
- good weldable

### Target Industries

- food engineering
- electrical engineering
- mechanical engineering
- vacuum technology
- medical technology
- automotive industry
- chemical technology
- precision engineering
- conveyor technology

### Mechanical properties

<b>parameter</b>	<b>value</b>	<b>unit</b>	<b>norm</b>	<b>comment</b>
Modulus of elasticity (tensile test)	1mm/min	2700	MPa	DIN EN ISO 527-2 1) (1) For tensile test: specimen type 1b
Tensile strength	50mm/min	89	MPa	DIN EN ISO 527-2 (2) For flexural test: support span 64mm, norm specimen.
Tensile strength at yield	50mm/min	89	MPa	DIN EN ISO 527-2 (3) Specimen 10x10x10mm
Elongation at yield	50mm/min	5	%	DIN EN ISO 527-2 (4) Specimen 10x10x50mm, modulus range between 0.5 and 1% compression.
Elongation at break	50mm/min	15	%	DIN EN ISO 527-2 (5) For Charpy test: support span 64mm, norm specimen.
Flexural strength	2mm/min, 10 N	122	MPa	DIN EN ISO 178 2) (6) Specimen in 4mm thickness
Modulus of elasticity (flexural test)	2mm/min, 10 N	2600	MPa	DIN EN ISO 178
Compression strength	1% / 2% 5mm/min, 10 N	15 / 28	MPa	EN ISO 604 3)
Compression modulus	5mm/min, 10 N	2300	MPa	EN ISO 604 4)
Impact strength (Charpy)	max. 7,5J	175	kJ/m <sup>2</sup>	DIN EN ISO 179-1eU 5)
Notched impact strength (Charpy)	max. 7,5J	4	kJ/m <sup>2</sup>	DIN EN ISO 179-1eA
Ball indentation hardness		167	MPa	ISO 2039-1 6)

### Thermal properties

<b>parameter</b>	<b>value</b>	<b>unit</b>	<b>norm</b>	<b>comment</b>
Glass transition temperature	188	°C	DIN 53765	1) (1) Found in public sources.
Melting temperature	n.a.	°C	DIN 53765	(2) n.a. = not applicable
Service temperature short term	180	°C		(3) Found in public sources.
Service temperature long term	160	°C		Individual testing regarding application conditions is mandatory.
Thermal expansion (CLTE)	23-60°C, long.	6	10 <sup>-5</sup> *K <sup>-1</sup>	DIN EN ISO 11359-1;2
Thermal expansion (CLTE)	23-100°C, long.	6	10 <sup>-5</sup> *K <sup>-1</sup>	DIN EN ISO 11359-1;2
Specific heat	1.2	J/(g*K)	ISO 22007-4:2008	
Thermal conductivity	0.21	W/(K*m)	ISO 22007-4:2008	

### Electrical properties

<b>parameter</b>	<b>value</b>	<b>unit</b>	<b>norm</b>	<b>comment</b>
Surface resistance	10 <sup>14</sup>	Ω	DIN IEC 60093	

### Other properties

<b>parameter</b>	<b>value</b>	<b>unit</b>	<b>norm</b>	<b>comment</b>
Water absorption	24h / 96h (23°C)	0.06 / 0.1	%	DIN EN ISO 62 1) (1) Ø ca. 50mm, h=13mm
Resistance to hot water/ bases	+			(2) Corresponding means no listing at UL (yellow card). The information might be taken from resin, stock shape or estimation. Individual testing regarding application conditions is mandatory.
Resistance to weathering	-			
Flammability (UL94)	corresponding to	VO	DIN IEC 60695-11-10;	2) (2)

Our information and statements reflect the current state of our knowledge and shall inform about our products and their applications. They do not assure or guarantee chemical resistance, quality of products and their merchantability in a legally binding way. Our products are not defined for use in medical or dental implants. Existing commercial patents have to be observed. The corresponding values and information are no minimum or maximum values, but guideline values that can be used primarily for comparison purposes for material selection. These values are within the normal tolerance range of product properties and do not represent guaranteed property values. Therefore they shall not be used for specification purposes. Unless otherwise noted, these values were determined by tests at reference dimensions (typically rods with diameter 40-60 mm according to DIN EN 15860) on extruded and machined specimen. As the properties depend on the dimensions of the semi-finished products and the orientation in the component (esp. in reinforced grades), the material may not be used without a separate testing under individual circumstances. The customer is solely responsible for the quality and suitability of products for the application and has to test usage and processing prior to use. Data sheet values are subject to periodic review, the most recent update can be found at [www.ensinger-online.com](http://www.ensinger-online.com). Technical changes reserved.

